

# **AVIENT SPECIALTY INKS**

#### PRODUCT INFORMATION BULLETIN



# 2530 Infinite FX Shimmer Base

2530 Infinite FX Shimmer Base is a crystal clear base specifically designed for printing shimmer and liquid metallic flakes. The shimmer base allows for infinite creativity in designs and can be mixed with multiple colored metallic flakes. 2530 Infinite FX Shimmer Base is a low-cure special effect with excellent adhesion and wash durability.

# **HIGHLIGHTS**

- Add metallic flakes to base for infinite designs
- Low-cure, save energy
- Tintable with plastisol colorants
- Use on various colored grounds and underbase for different effects
- Excellent adhesion to fabrics, stretch properties, and wash durability

### PRINTING TIPS

- Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results
- Mix up to 15% metallic flakes for the desired look, mix thoroughly
- Print in last position or flash after each print if using multiple screens
- Print direct to fabric or over a flashed-dried base plate. Use a suitable underbase when printing on garments prone to bleed
- Tintable with plastisol colorants. See Pigment Loading section for suggested tinting percentages. Adjust the % colorant added based on the strength of the colorants and color saturation desired
- Metallics reflect infrared heat and a forced air dryer is recommended for curing. If using an electric oven, extend dwell time to achieve proper cure
- Curing is a time and temperature process, a lower oven temperature setting with a slower belt speed while maintaining recommended ink cure temperature is always best to protect fabric, control dye migration and reduce energy consumption
- 2530 Infinite FX Shimmer Base can be cured between 270°F 320°F (132°C 160°C)
- Can be mixed with other Infinite FX HD bases or clears
- For cold-peel transfers, use a coated release paper or polyester film. Print using 70 duro squeegee and recommended mesh counts followed by adhesive. Gel at 212°F (100°C) for 60 sec. Apply transfer with heat press at 300°F (150°C) for 10-12 sec at medium pressure. For transfers on polyester, back with a low bleed white and/or blocker. Verify process.

# **COMPLIANCE**

- Non-phthalate
- For individual compliance certifications and conformity statements, please visit www.avientspecialtyinks.com/services/compliance-support

# **PRECAUTIONS**

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



AVIENT SPECIALTY INKS

V1.03 (Modified: 09/26/2024)

## RECOMMENDED PARAMETERS



## **Fabric Types**

100% cotton, blends, some synthetics



#### Mesh

Count: 86-160 t/in (34-62 t/cm) Tension: 25-35 n/cm2



# Squeegee

Durometer: 60/90/60, 60-70 Profile: Square, Sharp

Stroke: Hard flood, Medium stroke

Angle: 10-15%



#### Stencil


2 over 2

Off Contact: 1/16" (.2cm) Emulsion Over Mesh: 15-20%



#### Flash & Cure

Flash: 220°F (105°C) Cure: 270°F (132°C)



up to 10% Wilflex EQ up to 15% Wilflex RIO / MX up to 10% Rutland C3 Boosters

Entire Ink



# **Additives**



#### Storage

65-90°F (18-32°C) Avoid direct sunlight Use within one year of receipt



# Clean Up

Dispose unused ink responsibly. Standard plastisol cleaners, press wash, or ink degradant



#### **Health & Safety**

Find SDS information here: www.avient.com/resources/safety-data-sheets or contact your local CSR

2024, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application, volu have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner